Shree Ganesh Minerals Trade

Mr. Bhupat Patel
(Proprietor)
+91-8128758764

Mr. Ravi Patel
(Chief Marketing Officer)
+91-9537976442

Survey No. 180, House No. 106/A, Near Aiswarya Nagar, Navavas - Madhapar, Bhuj-Kutchh. 360020. (Gujarat)

# Foundry Grade Silica Sand Specification

## Silica Sand Chemical Composition

- $SiO_2$ - 98.00% Min
- $Fe_2O_3$ - 0.05% Max
- $Al_2O_3$ - 0.70% Max
- CaO - 0.20% Max
- $TiO_2$ - 0.05% Max
- MgO - 0.20% Max
- Clay - 0.50% Max
- Moisture - 0.50% Max (Dry Sand)

## Foundry Grade Silica Sand Granulometric Configuration:

| | | |
|---|---|---|
| Mesh 16 - 24 | Mesh 24 - 30 | AFS 30 - 35 |
| AFS 35 - 40 | AFS 40 - 45 | AFS 45 - 50 |
| AFS 50 - 55 | AFS 55 - 60 | AFS 60 - 65 |
| AFS 65 - 70 | AFS 70 - 75 | AFS 75 - 80 |
| AFS 80 - 85 | AFS 85 - 90 | AFS 100 - 120 |

## Mode Of Packing:

i) Loose Loaded in Trucks.

ii) In 50 kgs. PP Bag. (One time used or New, PP/HDPE Bags)

iii) In 1 MT Jumbo Bag. (One time used bags

We can supply tailor made material also as per customer's requirement.

Shree Ganesh Minerals Trade Madhapar, Bhuj

With Best Regards.

Email: info@sgmt.in | shreeganesh.mt@gmail.com
Web: www.sgmt.in | www.indiamart.com/shree-ganeshminerals.com